

モリブデンるつぼ (Straight Wall, Cover)

20-100ml 用まで、6 種類

With a melting point of 2610°C, molybdenum crucibles can be used for performing high temperature fusions in a vacuum or inert atmosphere.

Molybdenum crucibles exhibit excellent resistance to most acids, including sulfuric, hydrofluoric and hydrochloric, and are highly resistant to corrosion by many molten materials such as metals and glass.

Metal Technology offers a standard line of crucibles and covers from 20 ml to 100 ml and can also supply custom vessels and tubing.



CRUCIBLE DIMENSIONS					CRUCIBLES		COVERS	
CAPACITY ML	TOP DIA		DEPTH		PART NUMBER	PRICE EA US \$	PART NUMBER	PRICE EA US \$
	IN.	MM	IN.	MM				
20	1.32	33	1.14	29	40-0020SW	CALL	40-0015C	CALL
25	1.84	47	0.87	22	40-0025SW	CALL	40-0025C	CALL
35	1.84	47	1.14	29	40-0035SW	CALL	40-0025C	CALL
45	1.84	47	1.34	34	40-0045SW	CALL	40-0025C	CALL
55	1.84	47	1.60	41	40-0055SW	CALL	40-0025C	CALL
100	2.34	59	1.77	45	40-0100SW	CALL	40-0100C	CALL

Standard Wall Thickness: 0.035"

2018年1月ご発注分より適用（ユーザー価格）。

単価は、FOB 価格（オレゴン、アメリカ）で、メーカーより、アナウンスなく変動する可能性があります。

円価格（ユーザー価格）は、US\$ x 為替 x 個数 + 送料となります。表面仕上品（Acid Etch）は、US\$5/1 部品必要となり、御発注時に明記が必要です。

送料の目安は、50 個まで、15,000 円、100 個まで、20,000 円。その他経費として、海外送金手数料が、約 5,000 円かかります。

見積書にて、正式価格はお知らせします。商社様は、担当者まで、ご相談ください。